

## HIGH-PERFORMANCE EPOXY GROUT

### CHEMICAL RESISTANCE

**E = Suitable for immersion, spillage and fumes**

**S = Suitable for spillage and fumes**

**NR = Not Recommended**

REAGENT	EP15-GROUT
<b>ACIDS</b>	
Acetic Acid, 5%	E
Acetic Acid, 20%	S
Sulfuric Acid, 10%	E
Sulfuric Acid, 96%	NR
Hydrochloric Acid, 10%	E
Hydrochloric Acid, Conc.	S
Nitric Acid, 10%	E
Nitric Acid, Conc.	NR
Butyric Acid, 10%	E
Phosphoric Acid, 10%	E
Citric Acid, 10%	E
Linseed Oil Fatty Acid	S
Phenol Acid, 90%	E
Cresylic Acid	E
Naphthenic Acid	E
Boric Acid, 5%	E
Carbolic Acid	E
Oleic Acid	S
<b>ALKALIES</b>	
Sodium Hydroxide, 20%	E
Sodium Hydroxide, 50%	E
Ammonium Hydroxide, 10%	E
Ammonium Hydroxide, 29%	S
<b>SALTS</b>	
Barium Chloride	E
Aluminum Chloride	E
Magnesium Chloride	E
Ammonium Chloride	S
Ammonium Nitrate	S
Magnesium Sulfate	S
Sodium Phosphate	E
Sodium Thiosulfate	S

## HIGH-PERFORMANCE EPOXY GROUT

REAGENT	EP15-GROUT
<b>SALTS (cont'd.)</b>	
Iron Chloride	E
Sodium Hypochlorite	S
Sodium Sulfite, 1%	S
Calcium Hypochlorite	S
Calcium Chloride	E
Sodium Chloride	E
Sodium Sulfate	E
Trisodium Phosphate, 10%	E
Sodium Metasilicate, 10%	E
<b>MISCELLANEOUS</b>	
Mineral oil	E
Gasoline	E
High Flash Naphtha	E
Formaldehyde, 37%	E
Lard	E
Cottonseed Oil	E
Crude Oil	E
Hydrogen Peroxide, 20%	S
Styrene	NR
Kerosene	E
Vegetable Oil	E
Fish Oil	E
Fuel Oil	E
Motor Oil	E
Carbon Tetrachloride	S
Transmission Oil	E
Aliphatic Hydrocarbon	E
Chlorinated Hydrocarbon	S
Ethyl Alcohol	S
Butyl Alcohol	E
Nitrobenzene	NR
Ethylene Glycol	E
Ethyl Acetate	E
MEK	S
Coal Tar	E
Soap solution	E